AEROCELL - A

ECOTAPE

Class 'O' Nitrile



The High Quality Self Adhesive Nitrile Insulation Foam Tape

ECOTAPE

The High Quality Self Adhesive Nitrile Insulation Foam Tape



ECOTAPE is the flexible and self-adhesive insulation foam tape, which is made from Class 'O' Nitrile rubber elastomeric Closed Cell Insulation.

Ideal for wrapping hot or cold pipings and fittings. Energy saving and very easy to use. Excellent for preventing condensation problems. Designed specially for retarding heat loss in hot pipings and preventing heat gain or frost formation on cold, chilled water pipings or refrigeration lines.

Adheres firmly to all metals. No problem of delamination. ECOTAPE is specially coated with selected acrylic pressure sensitive adhesive providing long service life.

SPECIFICATION:

Size: 1/8" thick, 2" wide and 30' long per roll

 $3 \text{ mm(T)} \times 50 \text{mm (W)} \times 9.1 \text{ m} \pm 3\% \text{ (L)}$ (other sizes available on request.)

PACKAGING:

One roll of ECOTAPE is shrink wrapped and packed in one master carton (20 rolls in one carton)

PHYSICAL PROPERTIES:

Composition : Closed cell, Class 'O' Nitrile

rubber elastomeric

thermal insulation.

Color : Black

Density : 5 ± 1 pounds per cubic feet.

(0.06~0.10 g/cm³) ASTM D-1667

Thermal : 0.26 BTU. in/ft² hr. °F at 75 °F

Conductivity (0.04 W/mk at 24 °C)

(ASTM C-177)

Temperature Range : -20° F to $+200^{\circ}$ F

 $(-29^{\circ}\text{C to} + 93^{\circ}\text{C})$



THICKNESS TO PREVENT CONDENSATION:

Ambient Temperature and Relative Humidity	Pipe Temperature	
	50 °F (10 °C)	35 °F (2 °C)
80 °F (27 °C) & 50% RH	Single Layer	50% Overlap
85 °F (30 °C) & 70% RH	50% Overlap Plus Single Layer	50% Overlap Plus 50% Overlap

Tolerance - $3 \text{mm} \pm 0.5$

Corporate Office:

Plot No. 32, Sector-18 HUDA, Gurgaon - 122 015 Haryana. INDIA

Tel.: +91-124-4731500

Fax: +91-124-4731598, 4731599 E-mail: marketing@alpaeroflex.com.

Web: www.alpaeroflex.com



Plant

Bilaspur Road, Opp.Govt.P.G.College, Rudrapur Distt-U.S.Nagar (Uttarakhand) INDIA

Tel: +91-5944-247869, 247870

Fax: +91-5944243813